

Comparison Chart of Stainless Steel by International Standard

| Stainless steels | | | | | | | |
|------------------|------------------|-------|--------|------------------|------------------|---------------|-------------|
| 1.431 | X10CrNi18-8 | 301 | S30100 | | | | |
| 1.4318 | X2CrNiN18-7 | 301LN | | | | | |
| 1.4305 | X8CrNiS18-9 | 303 | S30300 | X10CrNiS18-9 | 202S 21 En58M | X10CrNiS18-09 | SUS 303 |
| 1.4301 | X2CrNi19-11 | 304 | S30400 | X5CrNi18-9 | 304S 15 | X5CrNi18-10 | SUS 304 |
| | X2CrNi18-10 | | | X5CrNi18-10 | 304S 16 | | SUS 304-CSP |
| | | | | XCrNi19-9 | 304S 18 | | |
| | | | | | 304S 25 | | |
| | | | | | En58E | | |
| 1.4306 | X2CrNi19-11 | 304L | S30403 | | 304S 11 | | SUS304L |
| 1.4311 | X2CrNiN18-10 | 304LN | S30453 | | | | |
| 1.4948 | X6CrNi18-11 | 304H | S30409 | | | | |
| 1.4303 | X5CrNi18-12 | 305 | S30500 | | | | |
| 1.4401 | X5CrNiMo17-12-2 | 316 | S31600 | X5CrNiMo17 12 2 | 316S 29 | X5CrNiMo17 12 | SUS 316 |
| 1.4436 | X5CrNiMo18-14-3 | | | X5CrNiMo17 13 3 | 316S 31 | X5CrNiMo17 13 | SUS316TP |
| | | | | X5CrNiMo 19 11 | 316S 33 | X8CrNiMo17 13 | |
| | | | | X5CrNiMo 18 11 | En58J | | |
| 1.4404 | X2CrNiMo17-12-2 | 316L | S31603 | | 316S 11 | | SUS316L |
| 1.4406 | X2CrNiMoN17-12-2 | 316LN | S31653 | | | | |
| 1.4429 | X2CrNiMoN17-13-3 | | | | | | |
| 1.4571 | | 316Ti | S31635 | X6CrNiMoTi1 7-12 | 320S 33 | | |
| 1.4438 | X2CrNiMo18-15-4 | 317L | S31703 | | | | |
| 1.4541 | | 321 | S32100 | X6CrNiTi18-10 | 321S 31 | | SUS321 |
| 1.4878 | X12CrNiTi18-9 | 321H | S32109 | | | | |
| 1.4512 | X6CrTi12 | 409 | S40900 | | | | |
| | | 410 | S41000 | | | | |